

Primo Primer - Instructions for Use

Safety: Always use safety glasses and a dust mask when working with Primo Primer.

By volume, mix 1 part Hotline Primo Primer to 5 parts water in a plastic container and mix well. Putting glass marbles in the container with the mix will help to remix the kiln wash as it settles.

Apply the primer evenly to the shelf or mould using a wide, soft bristled brush such as a hair brush. Apply 4 or 5 coats horizontally and vertically. Ensure the primer is kept well mixed as it settles very quickly.

Ensure the primer is completely dry before filling a mould or firing.

Cure primed shelf in a kiln at at least 288C for a minimum of 20 minutes. N.B. the primer colour will disappear at fusing and slumping temperatures.

Primo Primer is good for one firing. Re-apply for each firing.

After use the primer may be removed using a vacuum, brush or damp sponge. Leftover mix can be kept in a lidded plastic container, and must be well mixed before next use.