

© Quick Tip: Gold-Bearing Pink Tints



Samples of Ruby Red Tint (001824-0030-F) from various production dates.

To consistently reach target color when firing our gold-bearing striking glasses, Bullseye advises a pre-rapid heat soak of 2 hours at 1225°F (663°C) on the way up to process temperature. This applies to all forms of these glasses: sheet, billet, rod, frit, etc.

However, we've discovered something interesting in the process of testing our 1800 series of gold-bearing tint styles. It's possible to produce a variety of hues by firing these styles with a shorter pre-rapid heat soak hold of 30 minutes. Testing is required, since the color development varies in different production runs, and within a single production run.

Note that firing these styles with the 30-minute pre-rapid heat soak permanently affects color development. You may be able to continue developing color by firing again with a longer soak, but this will not push the glass to its target color.

1800 Series of Gold-Bearing Tints

Ruby Red Tint 001824-0030-F

Ruby Pink Tint 001831-0030-F

Burnt Scarlet Tint 001823-0030-F

Suggested Schedule for Gold-Bearing Glasses

Rate	Temperature	Hold
*	1225°F (663°C)	2:00
600°F (333°C)	1490°F (810°C)	:10
AFAP	900°F (482°C)	**

Shortened Pre-Rapid Heat Soak Schedule

Rate	Temperature	Hold
*	1225°F (663°C)	:30
600°F (333°C)	1490°F (810°C)	:10
AFAP	900°F (482°C)	**

* The initial rate of heat is not a critical factor in successfully striking gold-bearing glasses. Choose an initial rate of heat appropriate to the scale and design of the project that you are firing.

** Remainder of cycle depends on the thickness of the piece. Consult the *Bullseye Annealing Chart for Thick Slabs*. For color-sensitive projects, we recommend testing the cycle you plan to use by fusing a small sample of a similar setup in the same kiln as the project to best predict final color results.